PRODUCT DATA SHEET

PRi POWERGRIP



Multi-Purpose, Two Component, Epoxy Adhesive System

Applications

- Metal to metal and metal to glass bonding
- Plastic to plastic bonding
- Electronics, textile reed and handicrafts
- Automobiles | Construction | Engineering

Features - Benefits

- Superior bond strength
- Very low shrinkage
- Good chemical resistance



Mixing ratio by weight (R:H)	Pot life at 25°C 100 gm mass (Min)	Bond Strength (kg/cm ²) at 25 ^o C after 24 hrs.
100:80	60 - 80	Min 100

Coverage (sq. ft.)

Will vary based on surface and application

Mix Viscosity (mPas) at 25°C

30,000 - 45,000

Drying time (min) at 35°C

Surface dry	Touch dry	Hard dry
50 - 60	120 - 130	200 -220

SHELF LIFE

24 Month

PACKING

1.80kg (Resin 1 kg & Hardener 0.80 kg)

